TABLE TOP





PROPERTIES

- Moisture resistance panel
- High resistance to scratches, shocks and abrasion
- High maintenance of color
- One decorative face and one counterbalance kraft paper
- Straight edge with 2 mm ABS edge band











APPLICATIONS

- Suitable for horizontal intensive usage (table, office desk, kitchen...)

RANGE

: 57	Innofirst®	Innofirst®	Innofirst®
SIZE (mm)	1385x650	1650×850	1850×980
THICKNESS	28	28	28
PACK	10	10	10
PACKAGING	FULL PALET	FULL PALET	FULL PALET









TECHNICAL SPEC SHEET

TABLE TOP

TECHNICAL DATA SHEET

Mesured caracteristics	Table / Horizontal use	Test method	
Thickness	28 mm MR Complies with EN438 & DIN16926		
Wear resistance	Average wear ≥350 trs	NF D60 050 EN 438.2 DIN 53799	
Choc resistance (500 gr ball)	Drop height : 65 cm 80% without break Ø impression ≤ 1cm	NF D 60 050	
Scratch resistance	≥ 2 N	NF D 60 050 DIN 53799	
Resistance to dry heat (180°C)	Degree ≥3 (according to EN 12 722 - 1 to 5 degree)		
Cigarette burning resistance	Light brown colour autorised	EN 438.2 DIN 53799	
Resistance to hot liquids (cofee 80%)	Degree = 5 (1 to 5 degree)		
Shade stability (blue nbr 6 exposed)	Grey contrast ≥ 4 NF D 60 050		
Glue holding	Class 3		
Delamination resistance	≥ 1.0 Mpa	NF EN 13329	
Fire resistance	M3 Epiradiateur		
Formaldehyde content	3,5 mg/m²/h	ISO 12 460 - 3	

All this information can be amended any time as needed.

Distributor stamp		